



ELECTRO POWER ENTERPRISE
 11,12, B.G.CHAVIDA IND. ESTATE-2
 B/H-VISHAL ENGINEER, NR-SHRINATHJI ESTATE
 NUTAN NAGRIK BANK ROAD, CHANGODAR
 AHMEDABAD, GUJARAT, 382213.
 GSTIN: 24ABXPB1420D1Z7
 PHONE: 9825022936, 7600343075
 EMAIL: epe.rajesh@gmail.com/rajesh9825022936@gmail.com
 WEBSITE: www.electropowerenterprise.com

SR NO	TEST:	Sample on which heat test is not done	Properties after @300C for 8 hrs.	TEST METHOD
1	SHORE HARDNESS SHORE A	68	71	IS 3400 PART II
2	TENSILE STRENGTH (N/mm ²)	10.5 KG/CM ² MIN	88.2KG/CM ²	ASTM-D-412
3	ELONGATION AT BREAK % MIN	336 %	225 %	ASTM-D-412
4	TEAR (TYPE-C)	36 N/MM	26 N/MM	-----

- TEMPERATURE WITH STATE CAPACITY 250 DEGREES.